

Assorted grades as per EN 13489

Parquet flooring strip

MeisterParquet. longlife PS 300 | PS 500 (matt lacquered naturally oiled)

Characteristics as per EN 1310

Woods	Oak	Oak	American walnut						
Grading	vital	harm- onious	lively						
Botanical name	Quercus petraea (Matt.) Liebl.; Quercus robur L.	Quercus petraea (Matt.) Liebl.; Quercus robur L.	Juglans nigra						
Origin	Europe	Europe	North America						
Sound sap	✗	✗	✓						
Knots (live)	✓	≤ 10 mm Ø	✓						
Knothole dead knots	≤ 55 mm Ø	≤ 5 mm Ø	≤ 35 mm Ø						
Pin knots	✓	✓	✓						
Filler	✓	✓	✓						
Cracks, hairline cracks	✓	✓	✓						
Timber type typical bark inclusions	-	-	-						
Bark pockets	✗	✗	✗						
Slope of grain	✓	✓	✓						
Sound brown red heart	-	-	-						
Medulla rays rays	✓	✓	✓						
Colour variations	✓	✓	✓						
White streaks	✓	✓	-						
Stick marks	✗	✗	✗						
Infestation (EN 1311)	✗	✗	✗						

Explanations: Timber typical inclusions are, for example: resin pockets in larch, sugar pockets in maple; mineral inclusions. Wood is a natural product.

Variations in colour and structure can occur and indicate a solid wood product. All samples, brochures and photographs are therefore only approximations and not definitive. Exposure to sunlight also has an impact on the naturally occurring changes in timber shade. When it is delivered, wooden flooring can therefore look quite different to the sample supplied. The wood's tannins react to smoking; the colour of the wood therefore changes permanently to brown or a blackish dark brown. The varying tannic acid content results in colour variations on each plank, and from plank to plank, which again indicates that this is a natural product.

✓ = present ✗ = not present - = not relevant