

MeisterParquet. longlife PD 450 (matt lacquered)

Characteristics as per EN 1310

Woods	Oak	Oak							
Grading	harm- onious	lively							
Botanical name	Quercus petraea (Matt.) Liebl.; Quercus robur L.	Quercus petraea (Matt.) Liebl.; Quercus robur L.							
Origin	Europe	Europe							
Sound sap	X	X							
Knots (live)	≤ 15 mm Ø	≤ 45 mm Ø							
Knothole dead knots	≤10 mm Ø	≤ 35 mm Ø							
Pin knots	✓	✓							
Filler cracks	✓	✓							
Small cracks, hairline cracks, Lightning cracks	✓	✓							
Timber type typical bark inclusions	-	-							
Bark pockets	X	X							
Slope of grain	✓	✓							
Sound brown red heart	-	-							
Medulla rays	✓	✓							
Colour variations	✓	✓							
White streaks	✓	✓							
Stick marks	X	X							
Infestation (EN 1311)	X	X							

Explanations: Timber typical inclusions are, for example: resin pockets in larch, sugar pockets in maple; mineral inclusions.

Wood is a natural product.

Variations in colour and structure can occur and indicate a solid wood product. All samples, brochures and photographs are therefore only approximations and not definitive. Exposure to sunlight also has an impact on the naturally occurring changes in timber shade. When it is delivered, wooden flooring can therefore look quite different to the sample supplied. The wood's tannins react to smoking; the colour of the wood therefore changes permanently to brown or a blackish dark brown. The varying tannic acid content results in colour variations on each plank, and from plank to plank, which again indicates that this is a natural product.

✓ = present X = not present - = not relevant